



April 11, 2019

RMA Armament, Inc.
1479 Gillespie St. Suite 303
Rock Island, IL 61201
ATTN: Blake Waldrop

Dear Mr. Waldrop:

In accordance with your instructions, Oregon Ballistic Laboratories conducted Ballistic Resistance (V_0) testing on one sample.

The sample was tested in accordance with NIJ-STD-0101.06 Level IV (abbreviated) (modified) in an indoor range with the muzzle of the test barrel mounted 50 feet away from the target and positioned to produce 0-degree obliquity impacts. Four infrared light screens, in conjunction with time-based frequency counters, were positioned such that projectile velocity was measured 8.25 feet from the target. Penetrations were determined by examination of a 5.5-inch clay block mounted behind the test sample. Results for all testing performed for this purpose are summarized in the following table.

Test Sample			Ballistic Threat			Results		
OBL No.:	Serial No.:	Weight (lbs.)	Projectile	Shots	Velocity (fps)	Penetrations	BFD (mm)	Pass/Fail
21433	00001	4.78	.30cal. M2 AP	1	2879	0	39.63	<u>PASS</u>

Samples will be maintained at Oregon Ballistic Laboratories for 30 days and then discarded, unless other instructions are received. If you have any further questions or concerns, please contact us.

Sincerely,

A handwritten signature in cursive script, appearing to read 'Brandon Bertsch'.

Brandon Bertsch
Oregon Ballistic Laboratories